



SOLIDLITE PAINT

Water-based Emulsion Paint for Internal Use



BENEFITS

- > Excellent flow.
- > Consistent leveling feature (with brush or roller).
- > High opacity.
- > Smooth finish.
- > Excellent fungus resistance.

DESCRIPTION

SOLIDLITE PAINT is the ideal paint for interior wall surfaces as it comes in a wide variety of mood creating shades from the **SOLID SYMPHONY** color chart. The paint provides a smooth and durable emulsion finish on any masonry surfaces such as plaster, wallboards and brick finishes. Based on its special formula, the PVA based paint creates a long lasting impression on interior walls.

USES

- > Interior cement plaster.
- > Concrete stone.
- > Brick asbestos.

PACKING & COVERAGE

SOLIDLITE PAINT is available in 5 and 18 liter plastic bucket. Recommended thickness is around 30 μm (DFT) on a single coat. The product can potentially cover 0.3 liter / m^2 / 2 coats.

SHELF LIFE & STORAGE

SOLIDLITE will have a shelf life of 12 months in unopened container when kept in dry conditions at a temperature between 5 ~ 45 °C. Storage at higher temperature or high humidity may reduce shelf life. The product is best stored away from direct sun, heat and severe cold. Also, protect from freezing.

HEALTH & SAFETY

If skin or eye contact occurs, wash thoroughly with clean water and seek medical advice. Full health and safety details are given in product safety data sheet.



HOW TO USE

Surface must be clean, free from dust, grease, oil, etc. Patch joints and fill holes where necessary. All old loose, flaking or peeling paint must be removed.

Surface preparation for new walls:

Surface Preparation : Surface must be dry. **SOLIDLITE PAINT** may be applied directly to render or plaster surfaces. On plasterboard and over filling it is advisable to apply one coat of **SOLID ECOPRIME**, to reduce the difference in porosity of the joints. On old synthetic paint apply **SOLID ECOPRIME** after industry standard preparation.

Application : Mix well before use. Surface and air temperature during application must be above 5 °C and below 35 °C. Apply with brush or roller, diluting the product with up to 5% water, this is acceptable in hot weather and over absorbent surfaces. Typically two coats are required. Allow 4 ~ 8 hours between coats. Ensure each coat is fully dry before applying subsequent coats. The product is ready to use in its actual form. However, only if needed, dilute according to specification above.

Appearance : The finish for pale colours is a consistent flat finish, however some shading may appear in medium strong colours. **SOLIDLITE PAINT** has approximately the same finish as flat acrylic paint.

SOLIDLITE PAINT



QUALITY ASSURANCE

SOLID manufactures the entire range of construction chemical under compliance of SIRIM and other international standards (ASTM, BS, GBI, LEED).

TECHNICAL SERVICES

While new advance and changes will take place but one thing will never change is quality and meeting special needs of our customers. Our technical personnel and experts are available to provide additional information and technical assistance. We are eager to work with you in development of new product and resolve your problem.

Disclaimer : The information provided in the data sheets is based on both current development of work and years of field experience. Efforts are made to ensure that the information is reliable, however, we cannot accept the responsibility for any work carried out with our materials as we have no control over methods of application, site conditions etc. In view of continuing research and development (R&D) undertaken in our laboratories, we advise customers to ensure that the data sheets provided are not superseded by an updated publication. All products are sold are subject to our standard condition of sale, which is available on request. Field services, where provided, does not constitute supervisory responsibility. For additional information, please contact our local SOLID representative.



FACTORY OFFICE

Lot 772 (10-14), Jalan Subang 4, Kawasan Perindustrian Sg. Penaga
47620 Subang Jaya, Selangor Darul Ehsan, MALAYSIA.

+603-8081 4777 / 4776

+603-8081 4771

info@solidolutions.com.my www.solidolutions.com.my